



## Magnetic Particle Inspection

Product information

MR<sup>®</sup> 158-R Magnet powder concentrate

**MR**<sup>®</sup>  
CHEMIE  
NDT-materials

TO SEE MORE!

پترو فرهان گستر جنوب

## MR<sup>®</sup> 158-R Magnetic powder concentrate

fluorescent, 1:50, water suspendable  
for Magnetic Particle Inspection acc. to EN ISO 9934-1



### General appearance and composition:

- Water suspendable concentrate with fluorescent ferromagnetic particles
- Includes corrosion inhibitor and other additives
- Free of nitrite, halogen and silicone
- Medium particle size  $d_a = 1-3 \mu\text{m}$
- Yellow-green fluorescent under UV-radiation
- Sediment 0,20 – 0,30 ml / 100ml (1 h)
- Processing temperature: +10 °C to +80 °C
- No declaration of hazardous ingredients – ECO-LINE

### Relevant Specifications

- Type testing in accordance to EN ISO 9934 part 2
- Examination of corrosive ingredients according ASME Code V, Section V, art. 7
- In correspondence with Lloyd's Reg., Bureau Veritas, Det Norske Veritas, admitted by Framatome ANP

### Application:

- Remove tinder, rust and other contaminations from surface in a suitable manner
- Shake concentrate well
- Dilute 1:20 to 1:50 in water
- During magnetization (e.g. with a MR<sup>®</sup> Hand yoke) spray the preparation on the surface
- If using a test bench, fill the preparation into the container with the pump
- Under UV-radiation discontinuities will appear as yellow-green fluorescent magnetic particle indications

### Minimum shelf life:

- Will keep for a minimum of 1 year, stored at room temperature

### Pack sizes:

- 1 kg, 5 kg

FGJ-NDT.IR  
DIGINDT.IR

+982165565901

+982144584619

+989034119385

06.11.2014/db

\*\*Technical changes reserved!\*\*

MR<sup>®</sup> Chemie GmbH · Nordstr. 61-63 · 59427 Unna (Germany) · www.mr-chemie.de  
Tel.: +49 (0)2303 95151-0 · Fax: +49 (0)2303 95151-10 · e-mail: post@mr-chemie.de

1/1

NDT-materials  
CRACK  
Marker