



Fluxo
NDT products



Tehran, Tehransar

FLUXO P125

Water Washable Red Dye Penetrant - Sensitivity Level 2

General Appearance & Composition

- Water Washable and Solvent Removable Red Dye Penetrant
- Method A/C - Type 2 - Level 2 according to EN ISO 3452
- Low level of background / excellent washability
- **FLUXO P125** is a stable solution of petroleum distillates (high flash point), nonionic surfactants and red dyes.
- Processing Temperature: 0° to 50° C
- Associated products:
 - Cleaner / Remover: **FLUXO S190 / FLUXO N130**
 - Solvent Based Developer: **FLUXO R175 - FLUXO R180**
- Manufacturer: **SREM TECHNOLOGIES**

Approval & Specifications

- Sensitivity Level 2 according EN ISO 3452-2
- EN ISO 3452-2
- EN ISO 3452-6 (Low temperature)
- RCC-M Code
- ASME - Boiler and Pressure Vessel Code - Section V
- ASTM E 1417 - ASTM E 165
- Low in Sulphur & Halogens (Nuclear Quality)
- PMUC - Can be used in nuclear plants



Properties

- Aspect: Red Liquid
- Density (20° C): 0,855
- Flash Point: > 82° C
- Viscosity : 3 mm²/s (40° C)
- Compatible with any metal & many synthetic materials

Instructions for Use

- **Cleaning:** Remove rust, tinder and all contaminations from the part with **FLUXO** cleaner
- **Application of Penetrant:** Apply **FLUXO P125:** Application by immersion, spraying, brushing, dipping, etc... Allow to penetrate for at least 10 minutes.
- **Removal:** Remove the excess penetrant from the surface, with water. If you can't or don't want to use water, remove the excess penetrant with solvent **FLUXO S190** or remover **FLUXO N130**.
- **Drying:** Begin drying procedure immediately after water wash.
- **Developing:** Apply **FLUXO** developer on the part, achieving a thin and uniform layer.
- **Inspection:** Parts shall be inspected as per ISO 3059 standard requirements. Surface defects will appear as red indication.

Shelf Life

- Minimum of 5 years, stored at room temperature.
- Please refer to the Safety Data Sheet

Pack Sizes

- Aerosol Can 500mL
- Drum 1L - 5L - 10L - 200L

بتروفرهان گستر جنوب

FGJ-NDT.IR
DIGINDT.IR

+982165565901

+982144584619

+989034119385



Version: 09/2021

SREM TECHNOLOGIES

ZI Ouest - Rue des Frères Chappe - 72200 LA FLECHE - FRANCE - Tél +33 (0) 2.43.48.15.10 - Fax +33(0) 2.43.45.25.26 - www.srem.fr - info@srem.fr